CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-06-20-17** **Date: 16/07/2018**

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to drains at Bagalagunte old village (Surrounding of Maramma temple) in Bagalagunte in ward No.14

Agency : Sri. Ranganna.KM, No.05, 2nd cross, Siddeshwara Layout, Sidedahalli, Bangalore-72

Customer's Reference : EE/DD/WO/304/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-06-18

Sample ID No : 2018-06-20-17 /04

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/07/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/06/2018	16/07/2018	150.21 X 150.24 X 150.27	22568	8.294	426.5	18.9	17.9
2	PCC	M15	18/06/2018	16/07/2018	150.26 X 150.29 X 150.24	22583	8.228	386.2	17.1	
3	PCC	M15	18/06/2018	16/07/2018	150.28 X 150.20 X 150.25	22572	8.278	401.8	17.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು,
ಬಿ.ಬಿ.ಎಂ.ಪಿ ಉಪ****End of Report****
ಬಾಗಲಗುಂಟೆ, ಬೆಂಗಳೂರು

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : **CP-2018-04-21-02**

Date: 25/06/2018

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to drains at Bagalagunte old village (Surrounding of Maramma temple) in Bagalagunte in ward No.14

Agency : Sri. Ranganna.KM, No.05, 2nd cross, Siddeshwara Layout, Sidedahalli, Bangalore-72

Customer's Reference : EE/DD/WO/304/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-06-18

Sample ID No : 2018-06-20-17 /05

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/06/2018	25/06/2018	150.32 X 150.11 X 151.04	22564	8.168	250.5	11.1	11.5
2	PCC	M15	18/06/2018	25/06/2018	149.54 X 149.63 X 149.82	22375	8.286	266.3	11.9	
3	PCC	M15	18/06/2018	25/06/2018	149.81 X 149.72 X 150.54	22430	8.522	257.9	11.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Sig.....
Date.....

****End of Report****

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : **CP-2018-06-20-17**

Date: 16/07/2018

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to drains at Bagalagunte old village (Surrounding of Maramma temple) in Bagalagunte in ward No.14

Agency : Sri. Ranganna.KM, No.05, 2nd cross, Siddeshwara Layout, Sidedahalli, Bangalore-72

Customer's Reference : EE/DD/WO/304/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-06-18

Sample ID No : 2018-06-20-17 /06

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/07/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/06/2018	16/07/2018	150.25 X 150.28 X 150.20	22580	8.254	388.4	17.2	17.5
2	PCC	M15	18/06/2018	16/07/2018	150.24 X 150.25 X 150.28	22574	8.230	390.5	17.3	
3	PCC	M15	18/06/2018	16/07/2018	150.25 X 150.24 X 150.30	22574	8.212	408.6	18.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : **CP-2018-04-21-02**

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore. **Date: 25/06/2018**

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to drains at Bagalagunte old village (Surrounding of Maramma temple) in Bagalagunte in ward No.14

Agency : Sri. Ranganna.KM, No.05, 2nd cross, Siddeshwara Layout, Sidedahalli, Bangalore-72

Customer's Reference : EE/DD/WO/304/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-06-18

Sample ID No : 2018-06-20-17 /07

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/06/2018	25/06/2018	151.48 X 151.91 X 149.56	23010	8.208	269.2	11.7	12.0
2	PCC	M15	18/06/2018	25/06/2018	151.27 X 151.04 X 150.67	22847	8.006	283.3	12.4	
3	PCC	M15	18/06/2018	25/06/2018	149.86 X 151.73 X 149.31	22739	8.545	270.6	11.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Date: 16/07/2018

Lab ID	:	**CP-2018-06-20-17**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to drains at Bagalagunte old village (Surrounding of Maramma temple) in Bagalagunte in ward No.14
Agency	:	Sri. Ranganna.KM, No.05, 2nd cross, Siddeshwara Layout, Sidedahalli, Bangalore-72
Customer's Reference	:	EE/DD/WO/304/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-06-18
Sample ID No	:	2018-06-20-17 /08
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M15 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/07/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/06/2018	16/07/2018	150.20 X 150.24 X 150.19	22566	8.302	413.0	18.3	18.1
2	PCC	M15	18/06/2018	16/07/2018	150.28 X 150.27 X 150.28	22583	8.256	404.2	17.9	
3	PCC	M15	18/06/2018	16/07/2018	150.33 X 150.24 X 150.30	22586	8.272	408.8	18.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರ ಕಛೇರಿ
ಪೂರ್ವ ವಿಭಾಗ
ಬಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

Page 1/1
****End of Report****

Scanned by CamScanner